

SIGRAFINE® R7340

Material: Graphite

Forming: Isostatically pressed

Application: High-temperature application

Material data of SIGRAFINE® R7340

Typical properties	Units	Test standards	Values*
Average grain size	µm	ISO 13320	15
Bulk density	g/cm ³	DIN IEC 60413/204	1.72
Open porosity	Vol. %	DIN 66133	15
Medium pore entrance diameter	µm	DIN 66133	2.2
Coefficient of permeability (ambient temperature)	cm ² /s	DIN 51935	0.25
Rockwell hardness HR _{10/100}		DIN IEC 60413/303	80
Resistivity	µΩm	DIN IEC 60413/402	12
Flexural strength	MPa	DIN IEC 60413/501	45
Compressive strength	MPa	DIN 51910	90
Dynamic modulus of elasticity	MPa	DIN 51915	11 x 10 ³
Thermal expansion (20 - 200 °C)	K ⁻¹	DIN 51909	3.2 x 10 ⁻⁶
Thermal conductivity (20 °C)	Wm ⁻¹ K ⁻¹	DIN 51908	105
Ash content	ppm	DIN 51903	200

* Typical average values of different rectangular and round block sizes. The actual individual block values might vary depending on dimension and format. For any engineering/design purposes please always contact our technical sales team.

